



TECHNICAL DATA SHEET

Type	PRS10A		
Colour	White		
Fiber	100 % Polyester		
Material	Thermobonded		
Weight	ISO 9073-1	g/m ²	100
Thickness	ISO 9073-2	mm	10
Filter class	EN 779		G2
Initial arrestance	EN 779	%	58
Average arrestance	EN 779	%	75
Nominal air flow speed	EN 779	m/s	1,5
Initial pressure loss	EN 779	Pa	17
Final pressure loss	EN 779	Pa	250
Dust holding capacity	EN 779	g/m ²	633
Flammability	DIN 53438		F1 / M1

poirino spa

Via Riva, 25 - 14021 Buttigliera d'Asti (AT) Italy
Tel. +39 011 992.13.72 - Fax +39 011 992.13.93 - e-mail poirino@poirino.it